



topciment.com

PRIMACEM®



PRIMACEM® FLEX

Primer; bonding bridge between mortars

Primacem® Flex is a primer for use as a bonding bridge between new and old mortars, as well as for improving the bonding properties of all types of mortars.

Properties

- Improves adhesion between mortars.
- Easy to apply, ready-to-use product.

Performance

Its yield is 10-12m²/L

Technical information

PROPERTIES	SPECIFICATION	UNIT	METHOD
Nature	Styrene-Butadiene		
Aspect	Milky white liquid		
Non-volatile content	34-35	%	UNE-EN ISO 3251:2020
Density	1,02±0,05	g/cm ³	UNE-EN ISO 2811-1

Substrate preparation and application

The substrates must be clean and free of grease, oils, oxides, paint residues and loose or poorly adhering parts. Apply to the surface by brush, brush or sprayer. Cover the entire surface, trying to apply a uniform film and avoiding thick layers. Allow to dry until "tacking" for the application of the mortar. The application temperature should be between 5 -30° C, without excessive wind, and the substrate temperature should be between 5 -25° C.

Special precautions

It is essential to follow the instructions on the label of the container. For further information, please refer to the safety data sheet of the product. Empty containers must be disposed of in accordance with current legislation. To prevent the product from drying out or thickening, close the lid after each use.

Presentation

It comes in 5 and 25L containers.

Cleaning of tools

The tools are washed with water immediately after use.

Storage conditions

The product should be stored in its original closed container and protected from the weather at temperatures between 10°C and 30°C, in a dry and well ventilated place, away from heat sources and direct sunlight. The shelf life is 1 year from date of manufacture, properly stored.



The product must not be used for purposes other than those specified, without first having written instruction in its handling. It is always the responsibility of the user to take appropriate measures in order to comply with legislative requirements. The Safety Data Sheets of the product are available to the professional.

last edition: May 2024